

DurableBand™ -Plus anti-bending low water peak single-mode fiber is applied in 1260-1625nm all band transmission systems, with low loss at 1383nm, fully utilizing E-band transmission. DurableBand™ -Plus exceeds the requirements of ITU-T G.652.D and ITU-T G.657.A1 and is suitable for FTTH. 8.9 micron mode field diameter (MFD) ensures low splicing loss and high splicing efficiency, excellent mechanical properties and environmental characteristics ensure stable performance of optical fibers in various usage environments.

Optical Characteristics

Attenuation	
1310nm	≤0.35 dB/km
1383nm	≤0.33 dB/km
1550nm	≤0.21 dB/km
1625nm	≤0.23 dB/km

Point Discontinuity	
1310/1550nm	≤0.02dB

Cut-off Wavelength	
Cable cut-off wavelength (λcc)	≤1260nm

Mode Field Diameter (MFD)	
MFD at 1310nm	8.9±0.4μm



Macro bending Induced Attenuation			
Bending radius	Number of Turns	Wavelength	Attenuation
10mm	1	1550nm	≤0.75dB
10mm	1	1625nm	≤1.50dB
15mm	10	1550nm	≤0.25dB
15mm	10	1625nm	≤1.00dB

Dispersion	
Zero-dispersion wavelength	1300-1324nm
Zero-dispersion slope	0.073~0.092ps/nm²/km
Dispersionat 1550 wavelength	≤18.6ps/nm/km

Polarization Mode Dispersion	
Max. individual fiber PMD	≤0.2ps/√km
PMD link design value	≤0.1ps/√km

Geometric Characteristics

Geometrical Parameter	
Cladding diameter	125±0.7μm
Core/clad concentricity error	≤0.5μm
Cladding non-circularity	≤1.0%
Fiber curl R	≥4m
Coating diameter	245±10μm
Coating-Cladding Concentricity	≤10μm

Mechanical Characteristics

Proof Test	
Proof stress level	0.90GPa (1.3%, 130kpsi, 11.76N)

Strip Force	
Force (peak)	1.0N≤F≤8.9N
Force (average)	1.0N≤F≤5.0N

Tensile Strength	
Unaged (median; 0.5m)	≥3.80GPa (≥550kpsi)
Aged (median; 0.5m)	≥3.14GPa (≥460kpsi)

Dynamic fatigue parameters	
Fatigue	≥20

Environmental Characteristics

Test items	Conditions	Induced Attenuation at 1550, 1625nm
Temperature	-60°C to + 85°C	≤0.03dB/km
Water Immersion	+ 23°C/30Days	≤0.03dB/km
Steady damp-heat	+ 85°C/85%RH/30Days	≤0.03dB/km
Dry heat aging	+ 85°C/30Days	≤0.03dB/km

